

Surface Application Rates

Surfaces Types		Maximum Area Coverage (all coats, all products)		
		m ² per litre	feet ² per quart	feet ² per gallon
Basalt - Honed	Generic rate	10	0.8792	0.2454
Basalt - Polished	Generic rate	15	1.319	0.3681
Bluestone - Melbourne Basalt, Honed	Generic rate	10	0.8792	0.2454
Bluestone - Melbourne Basalt, Polished	Generic rate	15	1.319	0.3681
Bluestone - USA / Boston (Sandstone)	Generic rate	7	0.6154	0.1718
Bricks	Generic rate	7	0.6154	0.1718
Bricks	Fortifier Plus	7	0.6154	0.1718
Ceramic - Porous	Generic rate	8	0.7034	0.1963
Clay Paver	Generic rate	7	0.6154	0.1718
Concrete - Blockwork	Generic rate	5	0.4396	0.1227
Concrete - Blockwork	Fortifier Plus	5	0.4396	0.1227
Concrete - Engineered / Structural	Generic rate	2	0.1758	0.04908
Concrete - Engineered / Structural	Fortifier Plus	3	0.2638	0.07363
Concrete - Paver, Dry-Pressed	Generic rate	4	0.3517	0.09817
Concrete - Paver, Dry-Pressed	Fortifier Plus	4	0.3517	0.09817
Concrete - Paver, Wet Cast	Generic rate	7	0.6154	0.1718
Concrete - Paver, Wet Cast	Fortifier Plus	6	0.5275	0.1473
Concrete - Polished	Generic rate	15	1.319	0.3681
Concrete - Poured, Medium Porosity	Generic rate	7	0.6154	0.1718
Concrete - Poured, Medium Porosity	Fortifier Plus	6	0.5275	0.1473
Encaustic Cement Tile	Generic rate	5	0.4396	0.1227
Engineered Stone - Cementitious	Generic rate	7	0.6154	0.1718
Granite - Flamed	Generic rate	8	0.7034	0.1963
Granite - Honed	Generic rate	8	0.7034	0.1963
Granite - Leather	Generic rate	10	0.8792	0.2454
Granite - Polished	Generic rate	15	1.319	0.3681
Limestone - Honed	Generic rate	7	0.6154	0.1718
Limestone - Honed	Fortifier Plus	4	0.3517	0.09817
Limestone- Polished	Generic rate	12	1.055	0.2945
Marble - Honed	Generic rate	10	0.8792	0.2454
Marble - Leather	Generic rate	10	0.8792	0.2454
Marble - Polished	Generic rate	15	1.319	0.3681
Onyx - Polished	Generic rate	20	1.758	0.4908
Porcelain - Honed	Generic rate	15	1.319	0.3681
Porcelain - Polished	Generic rate	20	1.758	0.4908
Quartz - Man Made, Honed	Generic rate	15	1.319	0.3681
Quartz - Man Made, Polished	Generic rate	25	2.198	0.6136
Quartzite - Honed	Generic rate	8	0.7034	0.1963
Quartzite - Polished	Generic rate	15	1.319	0.3681
Render	Generic rate	5	0.4396	0.1227
Render	Fortifier Plus	6	0.5275	0.1473
Saltillo	Generic rate	5	0.4396	0.1227
Saltillo	Fortifier Plus	5	0.4396	0.1227
Sandstone - Dense (Indian)	Generic rate	7	0.6154	0.1718
Sandstone - Dense (Indian)	Fortifier Plus	6	0.5275	0.1473
Sandstone - Very Porous (Australian)	Generic rate	4	0.3517	0.09817
Sandstone - Very Porous (Australian)	Fortifier Plus	4	0.3517	0.09817
Slate - Dense Black / Grey	Generic rate	12	1.055	0.2945
Slate - Porous Brown	Generic rate	8	0.7034	0.1963
Soapstone	Generic rate	15	1.319	0.3681
Terracotta - Dense	Generic rate	8	0.7034	0.1963
Terracotta - Very Porous	Generic rate	5	0.4396	0.1227
Terrazzo - Honed	Generic rate	10	0.8792	0.2454
Terrazzo - Polished	Generic rate	15	1.319	0.3681
Travertine - Honed	Generic rate	7	0.6154	0.1718
Travertine - Honed	Fortifier Plus	7	0.6154	0.1718
Travertine - Polished	Generic rate	12	1.055	0.2945
Travertine - Tumbled	Generic rate	10	0.8792	0.2454
Victorian Cement Tile	Generic rate	5	0.4396	0.1227